



12 May 05

MEGlobal
Sales Specifications for Ethylene Glycol Low Conductivity Grade
Specified Material: 00030499-S

Specification	Ethylene Glycol Low Conductivity
Purity, % wt, minimum	99.8
Diethylene Glycol, % wt, maximum	0.1
Acidity, ppm, maximum, as Acetic Acid	20
Iron, ppm, maximum	0.05
Chlorides, ppm, maximum	0.2
Water, % wt, maximum	0.1
Color, Platinum-Cobalt Units, maximum	5
Appearance	Pass

Typical values for specific Gravity (20/20C): 1.1151 to 1.1156
Typical values for Refractive Index at 20 C: 1.4305 to 1.4330
Ash <50 ppm

NOTICE: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**